

Granulated 0-0-14

PRODUCT SPECIFICATION

CHEMICAL ANALYSIS

Component	Expressed as	Typical (% w/w)	Guarantee (% w/w)
Potassium oxide equivalent	K ₂ O	14.0	14.0 (min)
Sulfur	S	19.0	19.0 (min)
Magnesium	Mg	3.6	3.6 (min)
Calcium	Ca	12.0	11.4 (min)
Chloride	Cl ⁻	1.86	2.95 (max)
Moisture	H ₂ O	0.4	-

PHYSICAL PROPERTIES

Component	Expressed as	Typical
Bulk density (tapped)	lb/ft ³	87.3
-	kg/m ³	1401
Bulk density (loose)	lb/ft ³	80.3
-	kg/m ³	1289
Drained angle of repose	Degree	34
Poured angle of repose	Degree	33

PARTICAL SIZE DISTRIBUTION

Tyler mesh	US mesh	Size (mm)	Typical
5-9	5-10	2-4	90-95%

To the best of Anglo American Woodsmith Ltd knowledge and belief the information contained is accurate and reliable as of the date compiled. This data sheet is a representation of the average properties of product analyses as tested on samples. Anglo American Woodsmith Ltd makes no representation, warranty or guarantee as to the information's accuracy, reliability, completeness or timeliness. It is the user's responsibility to determine the suitability and completeness of such information for the users own particular use or purposes. Anglo American Woodsmith Ltd does not accept any liability or any loss or damages that may occur from the use of the above information with respect to the product. For further information, please refer to safety data sheet (SDS (USA and Canada) dated March 2020 on <https://www.poly4.com/poly4/about/>.

Reviewed: 10/2021